UNIVERSIDADE DE SÃO PAULO
FACULDADE DE ODONTOLOGIA DE RIBEIRÃO PRETO

MICHELLE ALEXANDRA CHINELATTI

**Influência dos níveis de energia do laser Er:YAG na capacidade de ablação,
microdureza e morfologia da dentina superficial e profunda**

Ribeirão Preto
2008

MICHELLE ALEXANDRA CHINELATTI

**Influência da energia do laser Er:YAG na capacidade de ablação,
microdureza e morfologia da dentina superficial e profunda**

Tese apresentada à Faculdade de Odontologia de
Ribeirão Preto da Universidade de São Paulo para
obtenção do título de Doutor em Odontologia.

Área de Concentração: Odontologia Restauradora,
opção Dentística.
Orientadora: Prof.^a Dr.^a Regina Guenka Palma Dibb

Ribeirão Preto
2008

AUTORIZO A REPRODUÇÃO E DIVULGAÇÃO TOTAL OU PARCIAL DESTE TRABALHO, POR QUALQUER MEIO CONVENCIONAL OU ELETRÔNICO, PARA FINS DE ESTUDO E PESQUISA, DESDE QUE CITADA A FONTE.

Chinelatti, Michelle Alexandra

Influência da energia do laser Er:YAG na capacidade de ablação, microdureza e morfologia da dentina superficial e profunda. Ribeirão Preto, 2008.

76p. : il.; 30cm.

Tese de Doutorado apresentada à Faculdade de Odontologia de Ribeirão Preto/USP. Área de concentração: Odontologia Restauradora.

Orientador: Palma-Dibb, Regina Guenka

1. Laser Er:YAG. 2. Preparo cavitário. 3. Dentina. 4. Microdureza. 5. MEV.

Michelle Alexandra Chinelatti

Influência da energia do laser Er:YAG na capacidade de ablação, microdureza e morfologia da dentina superficial e profunda

Tese apresentada à Faculdade de Odontologia de Ribeirão Preto da Universidade de São Paulo para obtenção do título de Doutor em Odontologia.
Área de Concentração: Odontologia Restauradora, opção Dentística.

Aprovada em: ____/____/____

Banca Examinadora

Prof. Dr. _____

Instituição: _____ Assinatura: _____

Prof. Dr. _____

Instituição: _____ Assinatura: _____

Prof. Dr. _____

Instituição: _____ Assinatura: _____

Prof. Dr. _____

Instituição: _____ Assinatura: _____

Prof. Dr. _____

Instituição: _____ Assinatura: _____

Dedico este trabalho ao meu marido, Tiago, com amor, admiração e gratidão pela compreensão, incentivo, carinho e apoio incondicional. Mesmo distante, a certeza da sua colaboração foi um dos principais motivos que nortearam a minha escolha pelo curso. Dividir a vida com você faz com que ela seja bem melhor!

Aos meus pais, Antonio (*in memoriam*) e Aparecida, minhas fontes de amor, coragem e inspiração, que muito batalharam em prol do melhor para seus filhos e me ensinaram que o caminho a ser seguido, nem sempre o mais fácil, é aquele que leva à felicidade pessoal.

Ao meu irmão, André, que sempre demonstrou seu afeto por mim através de proteção, cuidados e preocupação. Hoje é responsável por proteger e cuidar das pessoas mais amadas por mim, os seus filhos Pedro e Marina.

AGRADECIMENTOS

À Prof.^a Dr.^a Regina Guenka Palma Dibb, que, nos anos de convivência, muito me apoiou e ensinou, contribuindo para meu conhecimento científico e crescimento pessoal.

À Universidade de São Paulo, representada pela Magnífica Reitora Prof.^a Dr.^a Suely Vilela.

À Faculdade de Odontologia de Ribeirão Preto-USP, representada pelo Diretor Prof. Dr. Oswaldo Luiz Bezzon.

À Presidente da Comissão de Pós-Graduação da FORP-USP, Prof.^a Dr.^a Léa Assed Bezerra da Silva.

Ao Coordenador do Programa de Pós-Graduação em Odontologia Restauradora da FORP-USP, Prof. Dr. Jesus Djalma Pécora.

À Coordenação de Aperfeiçoamento de Pessoal de Nível Superior (CAPES), do Ministério da Educação, pela concessão da bolsa de doutorado e pelo apoio financeiro para a realização desta pesquisa.

Ao secretário do Programa de Pós-Graduação em Odontologia Restauradora da FORP-USP, Carlos Feitosa dos Santos, pela competência e simpatia com que realiza seu trabalho e sempre ajuda os alunos.

Às funcionárias da Seção de Pós-Graduação da FORP-USP, Isabel Cristina Galino Sola e Regiane Cristina Moi Sacilotto, pela paciência ao atenderem as constantes solicitações dos alunos.

A todos os alunos de Pós-Graduação do Departamento de Odontologia Restauradora da FORP-USP, por compartilharem nossas dúvidas, incertezas e alegrias ao longo do curso.

Ao Chefe do Departamento de Odontologia Restauradora da FORP-USP, Prof. Dr. Ricardo Gariba Silva, por colocar à disposição os laboratórios de pesquisa do departamento.

Aos Docentes do Departamento de Odontologia Restauradora da FORP-USP, pelos ensinamentos transmitidos.

À funcionária do Laboratório de Pesquisa em Dentística do Departamento de Odontologia Restauradora da FORP-USP, Patrícia Marchi, pela ajuda e atenção sempre demonstradas.

Ao funcionário do Laboratório de Pesquisa em Laser do Departamento de Odontologia Restauradora da FORP-USP, Reginaldo Santana Silva, pelo auxílio durante a realização da fase inicial deste trabalho.

Às funcionárias do Departamento de Odontologia Restauradora da FORP-USP, Maria Amália Viesti de Oliveira, Maria Izabel C. Francisco Miguel, Takami Hirono Hotta, Rosangela Angelini e Luíza Godoi Pitol, pelo carinho e apoio dados em várias fases do curso.

Às Profas. Dras. Silmara Aparecida Milori Corona e Maria Cristina Borsatto, pela amizade convívio e orientação em muitas atividades acadêmicas.

Ao mestrando Walter Raucci Neto pela parceria, paciência e tolerância em todas as fases desta pesquisa.

Às companheiras da pós, “Jú Faraoni” e “Dani Chimello”, por dividirem, desde o mestrado, essa jornada, que se tornou ainda mais valiosa quando compartilhada, mais recentemente, pela Vivian, Alessandra, Dani Messias, Carol, Silvinha e Cristiane, e pelo César, Fernando, Daniel, Juliano, Marcelo, Renato...

Às grandes amigadas que nasceram na FORP-USP: Renata Ramos, Carolina Torres, Juliane Ciccone, Wanessa Zaroni, Rodrigo Galo, Márcio de Menezes, Marta Contente, Fátima Rizoli, Jaciara Miranda, Andréa Ortolan...

Ao Prof. Dr. Vanderlei Salvador Bagnato, do Grupo de Óptica do Instituto de Física de São Carlos – USP, por gentilmente disponibilizar o equipamento de laser para a realização de uma das fases experimentais deste trabalho.

Ao Prof. Dr. Alberto Moreira Jorge Jr. e à Sra. Helena Racy, do Laboratório de Caracterização Estrutural do Departamento de Engenharia de Materiais da Universidade Federal de São Carlos, pelo auxílio na realização da fase inicial do projeto envolvendo microscopia eletrônica de varredura.

Ao Dr. Rodrigo Ferreira Silva, do Departamento de Química da Faculdade de Filosofia, Ciências e Letras de Ribeirão Preto – USP, pela colaboração na realização da fase final do projeto envolvendo microscopia eletrônica de varredura.

RESUMO

CHINELATTI, M. A. **Influência dos níveis de energia do laser Er:YAG na capacidade de ablação, microdureza e morfologia da dentina superficial e profunda.** 2008. 76p. Tese (Doutorado) – Faculdade de Odontologia de Ribeirão Preto, Universidade de São Paulo, Ribeirão Preto, 2008.

O objetivo do presente estudo foi avaliar *in vitro* a influência dos níveis de energia do laser de Er:YAG para preparo cavitário na capacidade de ablação, microdureza e morfologia da dentina superficial e profunda. Foram selecionados 72 terceiros molares humanos hígidos, que tiveram as raízes removidas e as coroas seccionadas no sentido vestibulo-lingual, obtendo-se 144 fragmentos. Os fragmentos foram alocados aleatoriamente em 2 grupos: dentina superficial (as faces oclusais foram lixadas até 1 mm abaixo da junção amelo-dentinária - JAD) e dentina profunda (2 mm abaixo da JAD). Posteriormente, cada grupo foi subdividido em 6 subgrupos (n=12) de acordo com as energias do laser de Er:YAG utilizadas (160, 200, 260, 300 ou 360 mJ, ou controle- sem irradiação). Para avaliar a capacidade de ablação, a massa (mg) de cada fragmento foi obtida antes e depois da irradiação. Para a realização do teste de microdureza Knoop, após a irradiação as cavidades foram incluídas em resina acrílica e seccionadas longitudinalmente. As marcações (10 g; 20 s) foram localizadas a 20, 40, 60, 80, 100 e 200 μ m abaixo da parede de fundo do preparo ou da margem superior dos espécimes do grupo controle. A análise morfológica foi realizada em MEV. Os valores de perda de massa e microdureza foram analisados individualmente pelos testes de ANOVA e Fisher ($\alpha=5\%$). Os resultados revelaram um aumento gradativo e significativo na perda de massa quando se aumentou a energia do laser utilizada, independente do tipo de dentina irradiada, sendo que a energia de 360 mJ apresentou maiores valores e foi estatisticamente diferente das demais energias estudadas. Em relação a profundidade da dentina não observou-se diferença significativa entre elas. A análise morfológica evidenciou que a ablação foi mais

seletiva na dentina profunda em que ocorreu mais intensamente a ablação da dentina intertubular, apresentando a protrusão dos túbulos dentinários, contudo, a energia de 360 mJ o aspecto morfológico da dentina profunda foi semelhante a superficial. Podendo assim concluir-se que o aumento da energia do laser proporcionou maior perda de massa, independente da profundidade da dentina, contudo, morfolologicamente pôde-se observar que a dentina profunda promoveu uma ablação seletiva, com menor remoção da dentina peritubular. Em relação à microdureza, as médias da dentina superficial foram significativamente superiores às da dentina profunda. As energias de 160 e 360 mJ foram diferentes entre si e das demais. Houve diferença entre todos os pontos medidos. Não foram observadas alterações morfológicas marcantes. Concluiu-se que a capacidade de ablação não depende da profundidade dentinária; a microdureza diminuiu com o aumento da energia, porém aumentou em relação às profundidades. A energia de 160 mJ promoveu um aumento nos valores de microdureza da dentina superficial na região mais próxima do preparo; a microdureza da dentina profunda não foi alterada quando foram utilizadas as energias de 160 e 200 mJ, enquanto os níveis de energia superiores promoveram uma diminuição na microdureza das dentinas superficial e profunda.

Palavras-chave: laser Er:YAG; ablação; dentina; preparo cavitário; microdureza dentinária; morfologia dentinária.

ABSTRACT

CHINELATTI, M. A. **Influence of Er:YAG laser energy levels on ablation rate, microhardness and morphology of superficial and deep dentin.** 2008. 76 p. Thesis (Doctorate) – School of Dentistry of Ribeirão Preto, University of São Paulo, Ribeirão Preto, 2008.

This study evaluated the ablation rate and the subsurface microhardness of superficial and deep dentin irradiated with different Er:YAG laser energy levels, and observed the micromorphological aspects of the lased substrates by means of Scanning Electron Microscopy (SEM). Seventy-two molar crowns were bisected, providing 144 specimens, which were randomly assigned into two groups (superficial or deep dentin) and later into six subgroups (160, 200, 260, 300, or 360mJ, or control- not irradiated). Initial masses of the specimens were obtained before irradiation. After laser irradiation, final masses were obtained and cavities were longitudinally bisected in half, being one hemi-section destined to SEM analysis and the other to the Knoop microhardness test. Microhardness measurements were performed at six points (20, 40, 60, 80, 100, and 200 μm) under the middle of the cavity floor. Data were submitted to ANOVA and Fisher's LSD Multiple-Comparison Tests ($\alpha=0.05$). There was no difference between ablation rate of superficial and deep dentin; a significant and gradual increase in the mass-loss values was reached when energies were raised, regardless the dentin depth; the energy level of 360 mJ showed the highest ablation rate and was statistically different to the other energies. SEM images showed that deep dentin was more selectively ablated, especially intertubular dentin, promoting tubule protrusion; at 360 mJ, the micromorphological aspect was similar for both dentin depths. Superficial dentin presented higher microhardness than deep dentin; 160 mJ resulted in the highest microhardness values and 360 mJ the lowest ones; 200 mJ was lower than 160 mJ and the control, but it was higher than 260 and 300 mJ, which presented similar means. Values at all points were different,

exhibiting increasing microhardness throughout; superficial dentin microhardness was the highest at 20 μm with 160 mJ, while the other energies demonstrated lower values than the control at all points; on deep dentin, 160 and 200 mJ were similar to the control, and other energies promoted significantly lower values. It may be concluded that the ablation rate did not depend on the depth of the dentin; an energy level lower than 360 mJ is recommended to ablate either superficial or deep dentin effectively without causing tissue damage. The lowest energy level increased superficial dentin microhardness at the closest extension under the cavity preparation; deep dentin subsurface microhardness was not altered by 160 and 200 mJ, while higher energy levels reduced subsurface microhardness of both superficial and deep dentin.

Key words: Er:YAG laser; ablation; dentin; cavity preparation; dentin microhardness; dentin morphology.

SUMÁRIO

1. Introdução.....	14
2. Proposição	19
3. Capítulo 1	21
3.1 Ablation rate and morphology of superficial and deep dentin irradiated with different Er:YAG laser energy levels	22
4. Capítulo 2	43
4.1 Effect of Er:YAG laser energies on superficial and deep dentin microhardness.....	44
5. Conclusões Gerais	65
Referências Bibliográficas	67
Anexos	

Introdução

1. INTRODUÇÃO

A realização do preparo cavitário, por meio do corte ou desgaste da estrutura dental utilizando instrumentos rotatórios adaptados em turbinas de baixa e alta-rotação, é baseada em princípios mecânicos e biológicos. Entretanto, estes instrumentos quase sempre causam desconforto e estresse ao paciente, por proporcionarem vibração, pressão e ruído, que frequentemente são acompanhados de dor.

Pesquisas com novas tecnologias para a realização de preparos cavitários vem sendo desenvolvidas com o objetivo de diminuir esse estresse, minimizar o desgaste de estrutura dental sadia e proporcionar uma superfície mais adequada para a adesão dos materiais restauradores (VISURI et al., 1996; KATAUMI et al., 1998; MARTINEZ-INSUA et al., 2000; TAKAMORI et al., 2000; CORONA et al., 2001; PALMA-DIBB et al., 2003; RAMOS et al., 2002; MONGHINI et al., 2004; SOUZA et al., 2004). O laser é uma destas tecnologias emergentes para o preparo cavitário (DOSTALOVA et al., 1998; HIBST, 2002; TAKAMORI et al., 2003; ATTRILL et al., 2004; CHINELATTI, 2003; CHINELATTI et al., 2003, 2004), com características favoráveis no que se refere ao conforto do paciente, podendo, em muitos casos, eliminar a necessidade de anestesia (KELLER ; HIBST, 1995; COZEAN et al., 1997).

O laser Er:YAG possui como meio ativo um cristal de ítrio-alumínio (Yttrium-Aluminum-Garnet) dopado com íons érbio, que uma vez estimulado por uma lâmpada de *flash* dentro de um ressonador, emite um comprimento de onda de 2,94 μm , que coincide com o pico máximo de absorção da água e dos radicais hidroxila presentes nos tecidos dentais, podendo ser aplicado em tecidos biológicos (KUMAZAKI et al., 1998; GIMBEL, 2000). Desta forma, ocorre a vaporização da água e dos componentes hidratados dos tecidos, causando um rápido aquecimento seguido por microexplosões resultantes do aumento da pressão interna das moléculas teciduais (HIBST; KELLER, 1989), que leva a ejeção do

substrato em forma de partículas microscópicas, gerando um efeito fotomecânico (KELLER; HIBST, 1995; MATSUMOTO et al., 1996). Esse processo de ablação consome a maior parte da energia irradiada, sendo liberada apenas uma pequena fração a estrutura dental remanescente (MATSUMOTO et al., 1996; HOSSAIN et al., 1999). Assim, desde que usado sob refrigeração ideal, o laser Er:YAG não causa danos térmicos a polpa dental (AOKI et al., 1998; HIBST, 2002; KIM et al., 2003; ATTRILL et al., 2004). Devido ao maior conteúdo de água na dentina, sua ablação é mais intensa do que a do esmalte quando se utiliza a mesma densidade de energia (HIBST; KELLER, 1989; SAKAKIBARA et al., 1994; JELINKOVA et al., 1996; ARMENGOL et al., 1999; MERCER et al., 2003). Da mesma forma, a ablação da dentina intertubular é maior do que a peritubular, pois apresenta maior quantidade de água (SAKAKIBARA et al., 1994; VISURI et al., 1996; ARMENGOL et al., 1999; SULEWSKI, 2000). Ainda, alguns estudos (HIBST; KELLER, 1989; AOKI et al., 1998) observaram maior ablação da dentina cariada, uma vez que esta apresenta alta permeabilidade e conseqüentemente é mais úmida do que a dentina hígida. Contudo, pouco se sabe sobre a atuação do laser Er:YAG em dentina profunda (SOUZA et al., 2004; FUENTES et al., 2004).

Em relação aos parâmetros do laser Er:YAG empregados para preparos cavitários, a energia merece destaque por estar diretamente relacionada a capacidade de ablação do substrato dental (MERCER et al., 2003; CORONA, 2003; MONGHINI et al., 2004) e a resistência adesiva dos materiais restauradores (RAMOS et al., 2002; MARTINEZ-INSUA et al., 2000; CHIMELLO et al., 2001; CEBALLOS et al., 2002). Alguns estudos (LI et al., 1992; JELINKOVA et al., 1996; SAKAKIBARA et al., 1994; MEHL et al., 1997; KATAUMI et al., 1998; SHIGETANI et al., 2002; CORONA, 2003) foram realizados na tentativa de padronizar os valores para que se obtenha uma ablação ideal e segura dos tecidos dentais mineralizados. No entanto, tais pesquisas ainda não resultaram em valores de aceitação comprovada. Apel et al. (2002) demonstraram que o laser Er: YAG proporciona uma diminuição na solubilidade

dos íons cálcio do esmalte dental, deixando a superfície ligeiramente desmineralizada. No entanto, alguns pesquisadores (ARIAMOTO et al., 1999; KATAUMI et al., 1998; ARMENGOL et al., 2000; CEBALLOS et al., 2002) observaram a presença de áreas de fusão e recristalização, tornando a superfície hipermineralizada e acido-resistente. Isso reduziria a permeabilidade do substrato dental e impediria a penetração de microrganismos cariogênicos, podendo diminuir a recorrência de cáries secundárias (CEBALLOS et al., 2001). Por outro lado, a pouca difusão de monômeros resinosos prejudicaria a adesão de materiais restauradores estéticos (KATAUMI et al., 1998; KAMEYAMA et al., 2000; HOSSAIN et al., 2000).

Uma maneira seguramente comprovada (ARENDS et al., 1980; KOULOURIDES ; HOUSCH, 1983) de avaliar as mudanças superficiais na densidade mineral e a realização de ensaios de microdureza dos tecidos dentais duros, nos quais um penetrador de diamante produz uma deformação característica de acordo com o tipo de ponta, cuja medida do comprimento define a profundidade de penetração. Assim, é possível estabelecer uma relação direta entre o grau de dureza de uma região e a profundidade de penetração da ponta ativa do aparelho (KIELBASSA et al. 1999). Contudo, os estudos de capacidade de ablação e microdureza empregando laser Er:YAG são escassos e as metodologias e parâmetros são diferentes, tornando-os insuficientes para que se possa chegar a uma conclusão a respeito da consistência das cavidades produzidas por esse tipo de laser. Do mesmo modo, os estudos ainda não são conclusivos com relação às alterações morfológicas superficiais do substrato dental após a ablação com laser Er:YAG. Através de análise em microscopia eletrônica de varredura pode-se verificar que a superfície dentinária apresenta irregularidades (VISURI et al., 1996; TANJI, 1998; MARTINEZ-INSUA et al., 2000) e exposição dos túbulos (VISURI et al., 1996; TANJI, 1998; AOKI et al., 1998). Aliás, diferentemente dos ácidos, o laser não desmineraliza a dentina, nem amplia a embocadura dos túbulos (MARTINEZ-INSUA et al.,

2000, CEBALLOS et al., 2001), podendo fusionar a rede de fibras colágenas da região basal da superfície irradiada, o que a torna destituída de espaços interfibrilares (CEBALLOS et al., 2002).

Diante das vantagens proporcionadas pelo laser Er:YAG em relação aos métodos convencionais para preparos cavitários, como diminuição de ruídos, vibrações e dor, sem causar danos ao tecido pulpar, são necessários estudos que avaliem as alterações da dentina superficial e profunda após a irradiação em diferentes energias do laser Er:YAG, visando a determinação de parâmetros adequados para a utilização deste equipamento. Daí a importância de avaliar a capacidade de ablação, a microdureza e a morfologia do substrato dentinário em diferentes profundidades na tentativa de buscar um método alternativo viável para realização de preparos cavitários.

Proposição

2. PROPOSIÇÃO

O presente estudo *in vitro*, composto por dois artigos científicos, teve como objetivos avaliar a influência da irradiação do laser Er:YAG utilizando diferentes níveis de energia indicados para a realização de preparos cavitários na:

- capacidade de ablação da dentina em diferentes profundidades (superficial e profunda);
- microdureza subsuperficial das paredes de fundo de cavidades realizadas em dentina superficial e profunda;
- morfologia das superfícies e subsuperfícies irradiadas.

Capítulo 1

3. CAPÍTULO 1

3.1. Ablation rate and morphology of superficial and deep dentin irradiated with different Er:YAG laser energy levels

Artigo científico enviado e considerado para publicação no periódico *Photomedicine and Laser Surgery* (Anexo 2).

ABSTRACT

Objective: This study evaluated the ablation rate of superficial and deep dentin irradiated with different Er:YAG laser energy levels, and observed the micromorphological aspects of the lased substrates by means of Scanning Electron Microscopy (SEM). **Background Data:** Little is known about the effect of Er:YAG laser irradiation on different dentin depths. **Methods:** Sixty molar crowns were bisected, providing 120 specimens, which were randomly assigned into two groups (superficial or deep dentin) and later into five subgroups (160, 200, 260, 300, or 360mJ). Initial masses of the specimens were obtained. After laser irradiation, final masses were obtained and mass losses were calculated followed by the preparation of specimens for SEM. Mass-loss values were submitted to two-way ANOVA and Scheffé and Fisher's LSD Multiple-Comparison Tests ($\alpha=5\%$). **Results:** There was no difference between superficial and deep dentin; a significant and gradual increase in the mass-loss values was reached when energies were raised, regardless the dentin depth; the energy level of 360 mJ showed the highest values and was statistically different to the other energies. SEM images showed that deep dentin was more selectively ablated, especially intertubular dentin, promoting tubule protrusion; at 360 mJ, the micromorphological aspect was similar for both dentin depths. **Conclusion:** the ablation rate did not depend on the depth of the dentin; an energy level lower

than 360 mJ is recommended to ablate either superficial or deep dentin effectively without causing tissue damage.

INTRODUCTION

Er:YAG laser has increasingly been used in operative dentistry¹⁻⁶, becoming a more comfortable method for patients during cavity preparations, as conventional cavity drilling may cause noise and pain.⁷⁻⁹ However, the time required for preparing cavities with the laser device is several times longer than the high-speed bur.^{10,11} In the clinic, this time may be reduced by increasing the energy level of laser irradiation for removing hard dental tissue, but the risk of thermal damage in the tissues may be increased.

Er:YAG laser irradiation removes both enamel and dentin due to its wavelength of 2.94 μm , which matches the absorption peak of water and is absorbed by hydroxyapatite, limiting the laser effect on these tissues to a superficial layer of a few micrometers, while sparing the surrounding tissues.¹²⁻¹⁶ This superficial layer can be heated up rapidly so that the pressure within the irradiated tissue abruptly increases until the strength of the substrate is surpassed. The overheated water is evaporated, resulting in a high steam pressure that causes microexplosions of tooth tissue, characterizing the thermomechanical ablation process.^{7,12,13} Since Er:YAG laser energy is well absorbed by water, the higher content of water in dentin facilitates the action of the laser, and the relatively predominant organic composition of dentin, became this tissue less resistant to laser ablation than enamel.^{12,17-21}

Basically, dentine consists of an organic matrix made up primarily of a hydrated type I collagen and an inorganic phase made up of a nanocrystalline-carbonated apatite²². Its characteristic microstructure consists of oriented tubules of 1-2 μm in diameter surrounded by highly mineralized (approx. 95 Vol% mineral phase) peritubular dentin embedded within a partially mineralized (approx. 30 Vol % mineral phase) collagen matrix (intertubular

dentin).²⁴⁻²⁶ In the arrangement of the dentin microstructure, the tubules run continuously between the enamel and the pulp and vary in density from about 15,000/mm² at the dentine-enamel junction (superficial dentin) to 65,000/mm² at the pulp (deeper dentine).²⁷ These marked differences in the various regions of a tooth, such as tubule density and peritubular and intertubular areas, distinguish superficial from deep dentin.^{24,27,28}

The apatite phase contributes to most of the compressive strength that might directly affect hardness, while the collagen phase provides elasticity²³. Changes in these two phases might contribute to changes in the physical properties, hardness and elasticity modulus of these biological composites. Since during irradiation with Er:YAG laser there is a non-uniform destruction of tooth structure and the ejection of both organic and inorganic tissue particles^{7,12,13}, it is necessary to evaluate Studying the mechanical properties of dental tissues after cavity preparations using Er:YAG laser, is important to verify whether or not occur alterations in their properties, such as microhardness, giving us an idea on how the mechanical behavior of the irradiated tissue under clinical loading conditions could be. Microhardness is defined as the resistance to local deformation based on the induced permanent surface deformation that remains after removing the load, being considered a supported method to evaluate superficial changes in the mineral density of hard dental tissues.

In this particular field of application, the literature available on the Er:YAG laser still presents varying parameters of energy settings, and, besides the fact that little is known about the effect of Er:YAG laser irradiation on different dentin depths,^{31,32} there are divergent results as well. Consequently, an optimal irradiation energy level should be determined to optimize the efficiency of Er:YAG laser for removing both superficial and deep dentin without affecting the microstructure of these substrates. Thus, the objective of this study was to evaluate the ablation rate of dentin as a function of Er:YAG laser energy level and substrate depth, and to observe the micromorphological aspects of the irradiated surfaces.

MATERIALS AND METHODS

Initially, this study was submitted to the Ethics Committee of the School of Dentistry of Ribeirão Preto, University of São Paulo, and initiated after being approved (process # 2005.1.656.58.1) (Anexo 1)..

- Experimental design

This study was composed of a randomized complete block design with 12 experimental specimens per *group / subgroup*. The variation factors examined were *dentin* at two levels (superficial and deep) and *energy* at five levels (160, 200, 260, 300 and 360 mJ). The response variable was *mass loss* numeric numbers in mg.

- Specimen obtainment

Extracted sound human third molars, coming from the Tooth Bank of the School of Dentistry of Ribeirão Preto, University of São Paulo, were used in this study. These teeth, kept in distilled water at 4°C for no longer than six months, were cleaned with scalpels and water/pumice slurry with dental prophylactic cups and examined under a 20X magnifier to discard those with structural defects. Then, sixty teeth were selected and their crowns and roots were separated by a cut 2 mm below the cemento-enamel junction with a water-cooled diamond saw in a precision cutting machine (Isomet 4000, Buehler GmbH, 40599 Dusseldorf, Germany).

The crown of each tooth was fixed with wax in an acrylic plate and sectioned longitudinally into two pieces in a bucco-lingual direction using a low-speed double-faced diamond disk (#7015, KG Sorensen, Barueri, 06454-920, Brazil). To reduce experimental error caused by the specimen condition,³³ half of each sectioned tooth crown was used as superficial dentin and the other half as deep dentin. Dentin discs were obtained by transversal

sectioning of the hemi-crowns with a low-speed diamond saw in a precision cutting machine under water irrigation. Superficial dentin was considered dentin within 0.5 mm of the enamel in the central occlusal groove, and deep dentin was defined as the dentin surface within 1.5 mm of the highest pulp horn. The method of obtaining both dentins was based in previous studies,^{29,30} but, according to our pilot study, a modification in the location of deep dentin was necessary to avoid pulp exposure during irradiation.

- Ablation rate assessment

The specimens of both superficial dentin and deep dentin groups were randomly assigned to five subgroups according to the irradiation energy used for preparing cavities: 160 mJ, 200 mJ, 260 mJ, 300 mJ and 360 mJ. The specimens were identified and individually stored in plastic containers with distilled water at 4°C for 24 hours, with the purpose of re-humidifying the substrate. After this period, the containers were kept at 37°C for 2 hours, and subsequently specimens were removed from the water, dried with absorbing paper for 20 seconds, and individually weighed in a precision analytical balance (Mettler, H54, Switzerland) with six decimal places of accuracy to determine the initial mass (m_1) in milligrams. Once the initial masses were recorded, the specimens were hydrated for 1 hour at room temperature. Before performing the irradiation, each specimen was fixed on an acrylic plate and a 3-mm-diameter ablation site was delimited by attaching a piece of insulating tape with a central orifice made by a punch.

The Er:YAG laser system used was the Twin Light operating at a pulse repetition rate of 3 Hz in non-contact and focused mode (irradiation distance of 12 mm), irradiation time of 30 seconds, and with the pulse energy levels described above. The water supply system was used throughout the irradiation time at a 2.5 mL/min flow. Once the irradiation was performed, the insulating tape was removed; the specimens were removed from the plates,

thoroughly cleaned and stored in distilled water for 1 hour. Then, the final masses (m_2) were recorded by individually weighing the specimens in the precision analytical balance following the same protocol described above. Dentin mass loss was calculated in milligrams by subtracting the final from the initial mass ($m_1 - m_2$). The amount of dentin removed during irradiation indicated the ablation rate under the experimental conditions tested.

-Statistical analysis

Data obtained from resulting amounts of dentin removed were analyzed by two-way ANOVA (factors: *dentin depth* and *energy*) and Fisher's LSD Multiple-Comparisons tests using a statistical software (NCSS/PASS Dawson edition, NCSS, Kaysville, Utah, 84037, USA) at a $\alpha=5\%$ significance level.

- Micromorphological analysis

After being weighed, the specimens were submitted to the micromorphological analysis of their laser-ablated surfaces by means of scanning electron microscopy. The preparation of the specimens was performed according to the following protocol: immersion in 2.5% glutaraldehyde (Merck KGaA, Frankfurter Str. 250, D-64293 Darmstadt, Germany) in an 0.1M sodium cacodylate buffer solution (pH 7.4) for 12 hours at 4°C; after fixation, the specimens were rinsed with an 0.1M sodium cacodylate (Merck KGaA, Frankfurter Str. 250, D-64293 Darmstadt, Germany) buffer solution several times and sequentially dehydrated in ethanol (Labsynth Produtos para Laboratório Ltda., Diadema-SP, Brasil) solutions, as follows: 25% for 20 min, 50% for 20 min, 75% for 20 min, 90% for 30 min and 100% for 60 min, after which they were immersed in a hexamethyldisilane (HMDS) solution (Merck KGaA, Frankfurter Str. 250, D-64293 Darmstadt, Germany) for 10 minutes, placed on absorbing paper inside glass plates and left drying in an exhaust system. Specimens were

mounted on metallic stubs with their ablated surfaces turned up, sputter-coated with gold (SDC 050, Bal-Tec AG, Foehrenweg 16, FL-9496 Balzers, Liechtenstein) and examined in scanning electron microscope (Philips XL30 FEG-SEM, Philips Electron Optics, Eindhoven, Holland) operating at 10 kV. The entire ablated surface of each specimen was scanned and the most representative areas were recorded in different magnifications.

RESULTS

Table 1. Analysis of variance table

Source term	DF	F-Ratio	Prob level	Power (alpha=0.03)
A: Dentin	1	0.62	0.433986	0.083385
B: Energy	4	35.78	0.000000*	1.000000
AxB	4	0.35	0.846853	0.085361

* Term significant at alpha = 0.03

Table 2. Ablation amount related to the factor energy

Energy (mJ)	Mean of mass loss (mg)
160	4.00000 ^d
200	4.42917 ^{cd}
260	5.85000 ^{bc}
300	6.67083 ^b
360	8.90000 ^a

Same superscript letters indicate statistical similarity

Table 3. Mean values and standard deviations of mass loss (mg) according to the dentin depth and energy level

	160 mJ	200 mJ	260 mJ	300 mJ	360 mJ
Superficial dentin	3.575 ^{A a} (1.28)	4.491 ^{AB a} (0.96)	5.775 ^{BC b} (1.86)	6.516 ^{C ce} (1.32)	8.916 ^{D d} (1.76)
Deep dentin	4.425 ^{E a} (2.15)	4.366 ^{E a} (1.54)	5.925 ^{F be} (1.43)	6.825 ^{F ce} (1.53)	8.883 ^{G d} (1.86)

Same superscript letters indicate statistical similarity.

Capital letters: to compare rows; Lower case: to compare columns.

- Ablation rate

The analysis of variance (Table 1) revealed that there was no significant difference between superficial and deep dentin (Fig. 1), there was a difference among the energies, and the interaction of the two factors was not significant. Comparing the energy levels, regardless of the dentin depth, there was an increase in the mass-loss values with an increase in the laser energy level (Fig. 2); 360 mJ provided the highest mass loss, which was significantly different from all the others; there was no difference between 160 and 200 mJ, between 200 and 260 mJ, and between 260 and 300 mJ (Table 2). The interaction dentin depth x energy (Table 3) showed that significantly higher mass-loss values were obtained with 360 mJ laser irradiation in either superficial or deep dentin (Fig. 3).

FIGURE 1. Amount (mg) of mass ablated as a function of the depth of dentin.

FIGURE 2. Amount (mg) of mass ablated as a function of the energy level (mJ), regardless of dentin depth.

FIGURE 3. Amount (mg) of mass ablated as a function of the energy level (mJ) and dentin depth.

- Micromorphological analysis

In deep dentin, laser irradiation at 160, 200, 260, and 300 mJ energy levels (Fig. 5.A, 5.B, 5.C, and 5.D, respectively) resulted in irregular surfaces with microcracks and higher removal of intertubular dentin, leaving the peritubular dentin with a protrusion aspect (tubule protrusion). This aspect was not observed in superficial dentin, which exhibited flat surfaces, and similar ablation of both intertubular and peritubular dentin at the same energy levels (Fig. 4.A, 4.B, 4.C, and 4.D).

Both in superficial and deep dentin (Fig. 4.E and 5.E, respectively), the energy of 360 mJ promoted flat surfaces with microcracks, no melting, and similar ablation of intertubular or peritubular dentin.

FIGURE 4. SEM images - micromorphological aspects of superficial dentin irradiated by Er:YAG laser according to the energy employed: **A- 160 mJ, B- 200 mJ, C- 260 mJ, D- 300 mJ, and E- 360 mJ:** flatter surfaces due to a non-selective ablation pattern, with microcracks in intertubular dentin (arrows), and no melting. **F-** control superficial dentin

FIGURE 5. SEM images - micromorphological aspects of deep dentin irradiated by Er:YAG laser according to the energy employed: **A- 160 mJ**, **B- 200 mJ**, **C- 260 mJ**, and **D- 300 mJ**: irregular surfaces, with microcracks (arrows) in intertubular dentin, no melting, and tubule protrusion (asterisks) due to a selective ablation of intertubular dentin. **E- 360 mJ**: flatter surface without tubule protrusion- a non-selective ablation pattern. **F-** control deep dentin

DISCUSSION

The ablation rate can be evaluated in terms of the amount of dental tissue removed within a given time³³ and is correlated with such parameters of irradiation as the number of pulses per second, energy per pulse, and duration of the treatment.³⁴⁻³⁷ The amount of tissue removed is thought to increase in proportion to the Er:YAG laser energy. However, with increased ablation efficiency, the dentin microstructure may be affected by the thermal effect and the resulting surface may vary from a white spot to charring, fusion, roughening, melting, recrystallization, cracking, and both de/remineralization and deproteinization.^{8,10,13,38-41} Researches^{34-36,42} indicate that adjustments to variable parameters, including irradiation time, water spray, pulse energy, and pulse repetition rate, should be made to improve the ablation ability of the laser. Moreover, different depths of dentin should be considered as additional variables affecting the ablation rate.

In this study, the ablation rate was not significantly influenced by dentin depth, and both superficial and deep dentin had a direct relationship with the laser energy resulting in higher tissue removal as the energy level was raised. In other words, if the energy levels are maintained constant, changing the dentin depth will not influence the amount of tissue removed. It can be understood that only one of these factors may influence the amount of dentin removed, that is, the energy level. This study supports previous statements^{36,40,42} that the ablation rate generally increases as a function of the energy level and adds new information concerning the dentin location. The explanation is based on the principle that the higher the energy per pulse on tooth tissue, the higher the energy density per pulse repetition, and, consequently, a higher inertial-confined heating of water creates enormous subsurface pressures that lead to the microexplosive removal of the surrounding mineral matrix and consequently more ablation of the tissue.^{35,43}

On the other hand, small increases in the energy levels did not result in significant amounts of dentin removed. These results suggest that, regardless of the dentin depth, there is a similar amount of tissue removed when the energy level is not highly increased. This behavior was previously described as saturation-type and shows the occurrence of a shielding resulting from ablation products not completely removed and deposited at the irradiated tissue.^{35,44} Diverging results were found by Shigetani et al.⁴² who obtained differences between 50 mJ and 100 mJ, and between 150 mJ and 200 mJ. This disagreement may be attributed to differences in laser devices, pulse repetition rates, and types of substrate employed.

Concerning the variation in the depth of the substrate, there was no difference between the mass losses of either superficial or deep dentin. Thus, variations in the water and mineral contents in dentin were not sufficiently significant to affect the gross amount of tissue removal. This fact probably is due to the absence of a significant influence of the mineralization degrees of superficial and deep dentin, therefore variations in microhardness were related to the decreased hardness near the pulp by a decrease in the hardness of the intertubular dentin matrix, which may be less mineralized.⁴⁵

However, the micromorphological analysis revealed that deep dentin was more selectively ablated than superficial dentin, exhibiting greater intertubular dentin removal, which characterizes the protruded aspect of the tubules indicating that peritubular dentin is more resistant to laser energy. This pattern can be explained by the fact that peritubular dentin has a high mineral content and lacks collagen as an organic matrix, different from the intertubular dentin, it makes up 92% of the collagen matrix.^{46,47} Moreover, such features are present mainly in the intertubular dentin located next the pulp.^{24,28,45} Another interesting micromorphological observation was made for both superficial and deep dentin ablated using the energy of 360 mJ, showing a flat surface resulting from similar ablation of both

intertubular and peritubular dentin, which means that this energy level promoted a non-selective ablation pattern.

The comparison of the results obtained in this study is difficult due to the scarceness of published studies about Er:YAG laser irradiation on superficial and deep dentin. Therefore, more studies need to be performed on this issue in an attempt to standardize the optimal parameters for tooth tissue ablation without compromising their intactness as well as their mechanical properties.

CONCLUSION

Based on the results of this study, it can be concluded that the ablation rate was not dependent on the dentin depth and was influenced only by the energy, which may be recommended at a level lower than 360 mJ to ablate both superficial and deep dentin effectively without damaging the integrity of the substrates; although variations in the depth of the substrate did not change the ablation rate, they influenced the selectiveness of the ablation, as deep dentin was more selectively ablated with minor removal of peritubular dentin.

REFERENCES

1. Dostálová, T., Jelinková, H., Krejsa, O., Hamal, K., Kubelka, J., Kugero,va, H., and Procházka, S. (1998). Noncontact Er:YAG laser ablation: clinical evaluation. *J. Clin. Laser Med. Surg.* 16, 273-282.
2. Hibst, R. (2002). Lasers for caries removal and cavity preparation: state of the art and future directions. *J. Oral Laser Appl.* 2, 203-211.

3. Takamori, K., Furukawa, H., Morikawa, Y., Katayama, T., and Watanabe, S. (2003). Basic study on vibrations during tooth preparations caused by high-speed drilling and Er:YAG laser irradiation. *Lasers Surg. Med.* 32, 25-31.
4. Attrill, D.C., Davies, R.M., King, T.A., Dickinson, M.R., and Blinkhorn, A.S. (2004). Thermal effects of the Er:YAG laser on a simulated dental pulp: a quantitative evaluation of the effects of a water spray. *J. Dent.* 32, 35-40.
5. Chinelatti, M.A., Ramos, R.P., Chimello, D.T., Borsatto, M.C., Pécora, J.D., and Palma-Dibb, R.G. (2004). Influence of the use of Er:YAG laser for cavity preparation and surface treatment in microleakage of resin-modified glass ionomer restorations. *Oper. Dent.* 29, 430-436.
6. Chinelatti, M.A., Ramos, R.P., Chimello, D.T., Corona, S.A., Pécora, J.D., and Palma-Dibb, R.G. (2006). Influence of Er:YAG laser on cavity preparation and surface treatment in microleakage of composite resin restorations. *Photomed. Laser Surg.* 24, 214-218.
7. Wigdor, H.A., Walsh, J.T., Featherstone, J.D., Visuri, S.R., Fried, D., and Waldvogel, J.L. (1995). Lasers in dentistry. *Lasers Surg. Med.* 16, 103-133.
8. Cozean, C., Arcoria, C.J., Pelagalli, J., and Powell, L. (1997). Dentistry for the 21st century? Erbium:YAG laser for teeth. *J. Am. Dent. Assoc.* 128, 1080-1087.
9. Bader, C., and Krejci, I. (2006). Marginal quality in enamel and dentin after preparation and finishing with an Er:YAG laser. *J. Dent.* 19, 337-342.
10. Hossain, M., Nakamura, Y., Tamaki, Y., Yamada, Y., Murakami, Y., and Matsumoto, K. (2003). Atomic analysis and knoop hardness measurements of the cavity floor prepared by Er,Cr:YSGG laser irradiation in vitro. *J. Oral Rehabil.* 30, 515-521.

11. Aoki, A., Ishikawa, I., Yamada, T., Otsuki, M., Watanabe, H., Tagami, J., Ando, Y., and Yamamoto, H. (1998). Comparison between Er:YAG laser and conventional technique for root caries treatment in vitro. *J. Dent. Res.* 77, 1404-1414.
12. Hibst, R., and Keller, U. (1989). Experimental studies of the application of the Er:YAG laser on dental hard substances: I. Measurement of the ablation rate. *Lasers Surg. Med.* 9, 338-344.
13. Matsumoto, K., Nakamura, Y., Mazeki, K., and Kimura, Y. (1996). Clinical dental application of Er:YAG laser for class V cavity preparation. *J. Clin. Laser Med. Surg.* 14, 123
14. Matsumoto, K., Wang, X., Zhang, C., and Kinoshita, J.I. (2007). Effect of a novel Er:YAG laser in caries removal and cavity preparation: A clinical observation. *Photomed. Laser Surg.* 25, 8-13.
15. Hossain, M., Nakamura, Y., Kimura, Y., Nakamura, G., and Matsumoto, K. (1999). Ablation depths and morphological changes in human enamel and dentin after Er:YAG laser irradiation with or without water mist. *J. Clin. Laser Med. Surg.* 17, 105-109.
16. Gimbel, C.B. (2000). Hard tissue laser procedures. *Dent. Clin. North Am.* 44, 931-953.
17. Kim, J.M., Kim, M.E., and Kim, K.S. (2005). Ablation rate and intrapulpal temperature by irradiation with Er:YAG laser. *Korean J. Oral Med.* 9, 375-381.
18. Jelinková, H., Dostalová, T., Krejsa, O., Hamal, K., Kubelka, J., and Procházka, S. (1997). The influence of Er:YAG laser ablation on cavity surface and cavity shape. *SPIE Proc.* 2672, 193-196.
19. Armengol, V., Jean, A., and Marion, D. (2000). Temperature rise during Er:YAG and Nd: YAG laser ablation of dentin. *J. Endodont.* 26, 138-141.

20. Mercer, C.E., Anderson, P., and Davis, G.R. (2003). Sequential 3D X-ray microphotographic measurement of enamel and dentine ablation by an Er:YAG laser. *Br. Dent. J.* 25, 99-104.
21. Lizarelli, R.F., Kurachi, C., Misoguti, L., and Bagnato, V.S. (1999). Characterization of enamel and dentin response to Nd:YAG picosecond laser ablation. *J. Clin. Laser Med. Surg.* 17, 127-131.
22. Raum, K., Kempf, K., Hein, H.J., Schubert, J., and Maurer, P. (2007). Preservation of microelastic properties of dentin and tooth enamel in vitro--a scanning acoustic microscopy study. *Dent. Mater.* 23, 1221-1228.
23. Kinney, J.H., Marshall, S.J., Marshall, G.W. (2003) The mechanical properties of human dentin: a critical review and re-evaluation of the dental literature. *Crit. Rev. Oral Biol Med.* 14, 13-29.
24. Marshall, G.W. Jr. (1993). Dentin: microstructure and characterization. *Quintessence Int.* 24, 606-617.
25. Balooch, G., Marshall, G.W., Marshall, S.J., Warren, O.L., Asif, S.A., and Balooch, M. (2004). Evaluation of a new modulus mapping technique to investigate microstructural features of human teeth. *J. Biomech.* 37, 1223-1232.
26. Habelitz, S., Rodriguez, B.J., Marshall, S.J., Marshall, G.W., Kalinin, S.V., and Gruverman, A. (2007) Peritubular dentin lacks piezoelectricity. *J. Dent. Res.* 86, 908-911.
27. Marshall, G.W., Marshall, S.J., Kinney, J.H., and Balooch, M. (1997). The dentin substrate: structure and properties related to bonding. *J. Dent. Res.* 25, 441-458.
28. Pashley, D. (1989). Dentin: a dynamic substrate-a review. *Scanning Microsc.* 3, 161-174.

29. Fuentes, V., Toledano, M., Osorio, R., and Carvalho, R.M. (2003). Microhardness of superficial and deep sound human dentin. *J. Biomed. Mater. Res. A.* 15, 850-853.
30. Toledano, M., Osorio, R., Osorio, E., Prati, C., and Carvalho, R.M. (2005). Microhardness of acid-treated and resin infiltrated human dentine. *J. Dent.* 33, 349-354.
31. Souza, A.E., Corona, S.A.M., Palma-Dibb, R.G., Borsatto, M.C., and Pécora, J.D. (2004). Influence of Er:YAG laser on tensile bond strength of a self-etching system and a flowable resin in different dentin depths. *J. Dent.* 32, 269-275.
32. Gonçalves, M., Corona, S.A., Palma-Dibb, R.G., and Pécora, J.D (2007). Influence of pulse repetition rate of Er:YAG laser and dentin depth on tensile bond strength of dentin-resin interface. *J Biomed Mater Res A.* Nov 1, [Epub ahead of print].
33. Kim, K.S., Kim, M.E., and Shin, E.J. (2005). Irradiation time and ablation rate of enamel in contact and non-contact irradiation with Er:YAG laser. *Photomed. Laser Surg.* 23, 216-218.
34. Mehl, A., Kremers, L., Salzmann, K., and Hickel, R. (1997). 3D volume-ablation rate and thermal side effects with the Er:YAG and Nd:YAG laser. *Dent. Mater.* 13, 246-251.
35. Lizarelli, R.F.Z., Moriyama, L.T., Jorge, J.R.P., and Bagnato, V.S. (2006). Comparative ablation rate from a Er:YAG laser on enamel and dentin of primary and permanent teeth. *Laser Phys.* 16, 849-858.
36. Corona, S.A.M., Souza, A.E., Chinelatti, M.A., Borsatto, M.C., Pecora, J.D., and Palma-Dibb, R.G. (2007). Effect of energy and pulse repetition rate of Er:YAG laser on dentin ablation ability and morphological analysis of the laser-irradiated substrate. *Photomed. Laser Surg.* 25, 26-33.

37. Corona, S.A., Souza, A.E., Chinelatti, M.A., Pecora, J.D., Borsatto, M.C., and Palma-Dibb, R.G. (2007). Influence of energy and pulse repetition rate of Er:YAG laser on enamel ablation ability and morphological analysis of the laser-irradiated surface. *J. Biomed. Mater. Res. A*. 84A, 569-575.
38. Ceballos, L., Osorio, R., Toledano, M., Tay, F.R., and Marshall, G.W. (2002). Bonding to Er:YAG laser treated dentin. *J. Dent. Res.* 81, 119-122.
39. Chimello-Sousa, D.T., Souza, A.E., Chinelatti, M.A., Pecora, J.D., Palma-Dibb, R.G., and Milori Corona, S.A. (2006). Influence of Er:YAG laser irradiation distance on the bond strength of a
- 40.
- 41.
- 42.
- 43.
44. restorative system to enamel. *J. Dent.* 34, 245-251.
- 40.45. Monguini, E.M., Wanderley, R.L., Pecora, J.D., Palma-Dibb, R.G., Corona, S.A., and Borsatto, M.C. (2004). Bond strength to dentin of primary teeth irradiated with varying Er:YAG laser energies and SEM examination of the surface morphology. *Lasers Surg Med.* 34, 254-259.
- 41.46. Ekworapoj, P., Sidhu, S.K., and McCabe, J.F. (2007). Effect of different power parameters of Er,Cr:YSGG laser on human dentine. *Lasers Med. Sci.* 22, 175-182.
- 42.47. Shigetani, Y., Okamoto, A., Abu-Bakr, N., and Iwaku, M. (2002). A study of cavity preparation by Er:YAG laser--observation of hard tooth structures by laser scanning microscope and examination of the time necessary to remove caries. *Dent. Mater. J.* 21, 20-31.

- 43.48. Lee, B.S., Lin, C.P., Hung, Y.L., and Lan, W.H. (2004). Structural changes of Er:YAG laser-irradiated human dentin. *Photomed. Laser Surg.* 22, 330-334.
- 44.49. Lizarelli, R.F., Moryiama, L.T., and Bagnato, V.S. (2003). Ablation of composite resins using Er:YAG laser--comparison with enamel and dentin. *Lasers Surg. Med.* 33, 132-139.
- 45.50. Kinney, J.H., Balooch, M., Marshall, S.J., Marshall, G.W. Jr., and Weihs, T.P. (1996). Hardness and Young's modulus of human peritubular and intertubular dentine. *Arch. Oral Biol.* 41. 9-13.
- 46.51. Senawongse, P., Otsuki, M., Tagami, J., and Mjör, I. (2006). Age-related changes in hardness and modulus of elasticity of dentine. *Arch. Oral Biol.* 51 , 457-463.
- 47.52. Bachmann, L., Diebolder, R., Hibst, R., and Zezell, D.M. (2005). Changes in chemical composition and collagen structure of dentine tissue after erbium laser irradiation. *Spectrochim. Acta A. Mol. Biomol. Spectrosc.* 61, 2634-2639.

Capítulo 2

4. CAPÍTULO 2

4.1. Effect of Er:YAG laser energies on superficial and deep dentin microhardness

Artigo científico submetido para publicação ao periódico *Lasers in Medical Science*
(Anexo 3)

ABSTRACT

This study evaluated the microhardness of superficial and deep dentin irradiated with different Er:YAG laser energies. Seventy-two molars were bisected and randomly assigned into two groups (superficial or deep dentin) and into six subgroups (160, 200, 260, 300, 360mJ, control). After irradiation, cavities were longitudinally bisected. Microhardness were performed at six points (20, 40, 60, 80, 100, 200 μ m) under the cavity floor. Data were submitted to ANOVA and Fisher's Tests ($\alpha=0.05$). Superficial dentin presented higher microhardness than deep dentin; 160mJ resulted in the highest microhardness and 360mJ the lowest ones. Values at all points were different, exhibiting increasing microhardness throughout; superficial dentin microhardness was the highest at 20 μ m with 160mJ; on deep dentin, 160 and 200mJ were similar to the control. The lowest energy increased superficial dentin microhardness at the closest extension under the cavity; deep dentin microhardness was not altered by 160 and 200mJ.

INTRODUCTION

Er:YAG laser has increasingly been used in operative dentistry [1-6], becoming a more comfortable method for patients during cavity preparations, as conventional cavity

drilling may cause noise and pain [7-9]. Er:YAG laser irradiation removes both enamel and dentin due to its wavelength of 2.94 μm , which matches the absorption peak of water and is absorbed by hydroxyapatite, limiting the laser effect on these tissues to a superficial layer of a few micrometers, while sparing the surrounding tissues [10-14]. This superficial layer can be heated up rapidly so that the pressure within the irradiated tissue abruptly increases until the strength of the substrate is surpassed. The overheated water is evaporated, resulting in a high steam pressure that causes microexplosions of tooth tissue, characterizing the thermomechanical ablation process [7, 10, 11]. Since Er:YAG laser energy is well absorbed by water, the higher content of water in dentin facilitates the action of the laser, and the relatively predominant organic composition of dentin, became this tissue less resistant to laser ablation than enamel [10, 15-19].

Basically, dentine consists of an organic matrix made up primarily of a hydrated type I collagen and an inorganic phase made up of a nanocrystalline-carbonated apatite [20]. Its characteristic microstructure consists of oriented tubules of 1-2 μm in diameter surrounded by highly mineralized (approx. 95 Vol% mineral phase) peritubular dentin embedded within a partially mineralized (approx. 30 Vol % mineral phase) collagen matrix (intertubular dentin) [21-23]. In the arrangement of the dentin microstructure, the tubules run continuously between the enamel and the pulp and vary in density from about 15,000/ mm^2 at the dentine-enamel junction (superficial dentin) to 65,000/ mm^2 at the pulp (deeper dentine) [24]. These marked differences in the various regions of a tooth, such as tubule density and peritubular and intertubular areas, distinguish superficial from deep dentin [21, 24, 25].

The apatite phase contributes to most of the compressive strength that might directly affect hardness, while the collagen phase provides elasticity [26]. Changes in these two phases might contribute to changes in the physical properties, hardness and elasticity modulus of these biological composites [27]. Since during irradiation with Er:YAG laser there is a non-

uniform destruction of tooth structure and the ejection of both organic and inorganic tissue particles [7, 10, 11], it is necessary to evaluate the mechanical properties of dental tissues after cavity preparations using Er:YAG laser, such as microhardness, giving us an idea on how the mechanical behavior of the irradiated tissue under clinical loading conditions could be. Microhardness is defined as the resistance to local deformation, based on the induced permanent surface deformation that remains after removing the load [28, 29]. It is considered a supported method to evaluate superficial changes in the mineral density of dental hard tissues [30, 31], as well as plays an important role in stress distribution when mastication forces are applied on a restored tooth [32].

The literature available on the Er:YAG laser still presents varying parameters of energy settings, and, besides the fact that little is known about the effect of Er:YAG laser irradiation on different dentin depths [33, 34], there are divergent results as well. Consequently, an optimal irradiation energy level should be determined to optimize the efficiency of Er:YAG laser for removing both superficial and deep dentin without damaging their mechanical properties. Thus, the objective of this study was to evaluate the ablation rate of dentin as a function of Er:YAG laser energy level and substrate depth, and to observe the micromorphological aspects of the irradiated surfaces. Thus, this study aimed to evaluate possible alterations in the microhardness of superficial and deep dentin after cavity preparations by Er:YAG laser with different irradiation energy levels.

MATERIAL AND METHODS

Initially, this study was submitted to the Ethics Committee of the School of Dentistry of Ribeirão Preto, University of São Paulo, and initiated after being approved (process # 2005.1.656.58.1) (Anexo 1).

Experimental design

This study was composed of a randomized complete block design with 12 experimental specimens per *group / subgroup*. The variation factors examined were *dentin* at two levels (superficial and deep), *energy* at six levels (160, 200, 260, 300 and 360 mJ, and control- not irradiated), and *subsurface point* at six levels (20, 40, 60, 80, 100 and 200 μm). The response variable was *Knoop microhardness* numeric numbers in kgf.

Specimen obtainment

Extracted sound human third molars, coming from the Tooth Bank of the School of Dentistry of Ribeirão Preto, University of São Paulo, were used in this study. These teeth, kept in distilled water at 4°C for no longer than six months, were cleaned with scalpels and water/pumice slurry with dental prophylactic cups and examined under a 20X magnifier to discard those with structural defects. Then, seventy-two teeth were selected and their crowns and roots were separated by a cut 2 mm below the cemento-enamel junction with a water-cooled diamond saw in a precision cutting machine (Isomet 4000, Buehler GmbH, 40599 Dusseldorf, Germany). The crown of each tooth was fixed with wax in an acrylic plate and sectioned longitudinally into two pieces in a bucco-lingual direction using a low-speed double-faced diamond disk (#7015, KG Sorensen, Barueri, 06454-920, Brazil). To reduce experimental error caused by the specimen condition [35], half of each sectioned tooth crown was used as superficial dentin and the other half as deep dentin. Dentin discs were obtained by transversal sectioning of the hemi-crowns with a low-speed diamond saw in a precision cutting machine under water irrigation. Superficial dentin was considered dentin within 0.5 mm of the enamel in the central occlusal groove, and deep dentin was defined as the dentin surface within 1.5 mm of the highest pulp horn. The method of obtaining both dentins was

based in previous studies [32, 36], but, according to our pilot study, a modification in the location of deep dentin was necessary to avoid pulp exposure during irradiation.

The specimens of both superficial dentin and deep dentin groups were randomly assigned into six subgroups, being five according to the irradiation energy used for preparing cavities (160 mJ, 200 mJ, 260 mJ, 300 mJ and 360 mJ) and one the control (without irradiation). The specimens were identified and individually stored in plastic containers with distilled water at 4°C for 24 hours, with the purpose of re-humidifying the substrate. Before performing the irradiation, each specimen was fixed on an acrylic plate and a 2-mm-diameter ablation site was delimited by attaching a piece of insulating tape with a central orifice made by a punch.

The Er:YAG laser system used was the Twin Light (Fotona Medical Lasers, Slovenia, Ljubljana) operating at a pulse repetition rate of 3 Hz in non-contact and focused mode (irradiation distance of 12 mm), irradiation time of 30 seconds, and with the pulse energy levels described above. The water supply system was used throughout the irradiation time at a 2.5 mL/min flow. Once the irradiation was performed, the insulating tape was removed; the specimens were removed from the plates and thoroughly cleaned. Specimens were individually placed in acrylic resin blocks to facilitate the bisection of cavities in their long axis, being one half destined to microhardness test and the other half to SEM analysis. Specimens of control subgroup did not receive laser irradiation; they were included and longitudinally bisected.

Microhardness test

To provide a more uniform surface for the reading and to improve the precision of the penetrations, the section-face of each hemi-specimen was ground with #1000- and #2000-grit SiC papers and polished with 0.3- and 0.05- μ m alumina suspensions. The polished hemi-

sections were cleansed with distilled water in an ultrasonic apparatus to remove any debris. Before testing microhardness, each specimen was placed on a plate and fixed with plastic wax using a parallelometer (ELQuip, São Carlos, SP, Brazil) to ensure that its surface was kept parallel to the horizontal plane. Knoop hardness was assessed using a microhardness tester (Shimadzu HMV-2000, Shimadzu Corporation, Kyoto, Japan). Settings for load and penetration were 10 g and 20 s. Penetrations were performed under cavity preparations at distances of 20, 40, 60, 80, 100, and 200 μm apart from the middle of the cavity floor or apart from the superior edge of control specimens. At each distance, three horizontally 100- μm -spaced measurements were performed and their mean was calculated.

Micromorphological analysis

The hemi-specimens destined to SEM analysis were prepared according to the following protocol: immersion in 2.5% glutaraldehyde in an 0.1M sodium cacodylate buffer solution (pH 7.4) for 12 hours at 4°C; after fixation, the specimens were rinsed with an 0.1M sodium cacodylate buffer solution several times and sequentially dehydrated in ethanol solutions, as follows: 25% for 20 min, 50% for 20 min, 75% for 20 min, 90% for 30 min and 100% for 60 min, after which they were immersed in a hexamethyldisilane (HMDS) solution for 10 minutes, placed on absorbing paper inside glass plates and left drying in an exhaust system. Specimens were mounted on metallic stubs with their longitudinal surfaces turned up, sputter-coated with gold and examined in scanning electron microscope operating at 20 kV. The region underneath the cavity floor (subsurface) was scanned and the most representative areas were recorded in different magnifications.

Statistical analysis

Data of dentin microhardness were analyzed by three-way ANOVA (factors: *dentin*, *energy* and *subsurface*) and Fisher's LSD Multiple-Comparisons tests using a statistical software (NCSS/PASS Dawson edition, NCSS, USA) at $\alpha=5\%$ significance level.

RESULTS

The variance analysis revealed that there was a significant difference between dentin depths, energies, subsurface points, and in the factor interactions. Fisher's LSD Multiple-Comparison Test showed that microhardness of superficial dentin was significantly higher than deep dentin (Fig. 1). Comparing the energy levels (Fig. 2), regardless of the dentin depth, the energy of 160 mJ resulted in the highest microhardness values, and 360 mJ the lowest ones; microhardness values of both dentins irradiated with 200 mJ were lower than 160 mJ and the control, and higher than those lased with 260 and 300 mJ, which presented similar means. Values at all subsurface points were different and exhibited increasing microhardness throughout (Fig. 3).

Figure 1. Overall means of subsurface microhardness according with the dentin depth.

Figure 2. Means of subsurface microhardness as a function of the energy level, regardless of the dentin depth.

Figure 3. Means of subsurface microhardness of both dentin depths as a function of the subsurface points.

The interaction dentin depth x energy (Fig. 4) showed that the significantly lowest microhardness values of either superficial or deep dentin were obtained with a laser irradiation of 360 mJ; microhardness of superficial dentin ablated with 160 mJ was significantly higher than both the control and that irradiated with the other energies; microhardness of deep dentin lased with 160 and 200 mJ was similar to the control, and that with 260 and 300 mJ was lower in comparison to the control deep dentin; superficial and deep dentin presented similar microhardness when both were irradiated either with 260 or 300 mJ.

Figure 4. Means of subsurface microhardness as a function of the dentin depth and the energy level

Table 1. Knoop microhardness means values of superficial dentin and standard deviations according to the energy levels and depths

<i>Subsurface/ Energy</i>	<i>20 μm</i>	<i>40 μm</i>	<i>60 μm</i>	<i>80 μm</i>	<i>100 μm</i>	<i>200 μm</i>
160 mJ	70.6 $\pm$ 1.2	64.9 ^a $\pm$ 1.7	66.2 ^b $\pm$ 1.7	67.7 ^c $\pm$ 1.9	69.1 ^d $\pm$ 1.5	70.1 ^e $\pm$ 1.4
200 mJ	61.9 $\pm$ 1	64.5 $\pm$ 0.6	65.5 $\pm$ 1	66.1 $\pm$ 1.2	67.1 $\pm$ 1.3	67.3 $\pm$ 1.2
260 mJ	59.4 $\pm$ 0.7	63.3 $\pm$ 0.8	64.6 $\pm$ 0.9	65.4 $\pm$ 0.8	66.2 $\pm$ 0.9	67.7 $\pm$ 1.3
300 mJ	59.4 $\pm$ 1.1	63.7 $\pm$ 0.7	64.8 $\pm$ 1	66.1 $\pm$ 1	66.3 $\pm$ 0.8	67.8 $\pm$ 0.6
360 mJ	58.3 $\pm$ 0.9	63.4 $\pm$ 0.9	64.8 $\pm$ 0.9	65.9 $\pm$ 0.8	66.8 $\pm$ 0.6	67.6 $\pm$ 0.6
control	63.8 $\pm$ 0.8	65.1 ^a $\pm$ 0.7	66.2 ^b $\pm$ 0.7	67.4 ^c $\pm$ 0.6	68.6 ^d $\pm$ 0.8	69.6 ^e $\pm$ 0.5

Same superscript letters indicate statistical similarity

Tables 1 and 2 display the microhardness of superficial and deep dentin, respectively, according to each subsurface point and energy. The interaction of all factors revealed that for superficial dentin irradiated with 160 mJ, the subsurface microhardness was higher than the control at 20 μm and similar at the remaining points; for deep dentin with 160 mJ, the subsurface microhardness was similar to the control at all points; the other energies resulted in lower values than control at all subsurface points of both superficial and deep dentin.

<i>Subsurface/ Energy</i>	<i>20 μm</i>	<i>40 μm</i>	<i>60 μm</i>	<i>80 μm</i>	<i>100 μm</i>	<i>200 μm</i>
160 mJ	62.5 ^a $\pm$ 1.1	63.9 ^b $\pm$ 0.8	65.8 ^c $\pm$ 0.8	67.2 ^d $\pm$ 0.8	68.2 ^e $\pm$ 0.8	69.7 ^e $\pm$ 0.9
200 mJ	62.3 ^{a,f} $\pm$ 1.2	62.8 ^{a,f} $\pm$ 1.2	64.6 $\pm$ 1.5	65.8 $\pm$ 1.1	67.1 $\pm$ 1.2	69.4 $\pm$ 1.1
260 mJ	60.5 $\pm$ 0.6	61.2 $\pm$ 0.8	63.8 $\pm$ 0.7	67.6 $\pm$ 0.8	69.2 $\pm$ 0.9	70.4 $\pm$ 0.8
300 mJ	60.1 $\pm$ 1.1	62.8 $\pm$ 0.9	65.2 $\pm$ 0.6	67.1 $\pm$ 0.8	68.3 $\pm$ 0.7	70.2 $\pm$ 0.8
360 mJ	59.2 $\pm$ 0.7	61.5 $\pm$ 0.7	63.4 $\pm$ 0.7	65.4 $\pm$ 1.2	67.6 $\pm$ 1.2	69.1 $\pm$ 0.5
control	62.7 ^{a,f} $\pm$ 1.	63.5 ^{b,f} $\pm$ 1.5	65.8 ^c $\pm$ 1.4	66.1 ^d $\pm$ 1.3	68.6 ^e $\pm$ 1.3	70.2 ^e $\pm$ 1.2

Table 2. Knoop microhardness means values of deep dentin and standard deviations according to the energy levels and depths

Same superscript letters indicate statistical similarity

SEM micrographs of subsurface of both superficial and deep dentin irradiated with 160, 200, and 260 mJ (Figs. 5, 6, 7, 8, 9, and 10, respectively) showed a corrugated and wave appearance with opened tubules and the absence of smear layer, and a crystalline-like aspect along the interfaces. The SEM micrographs of both dentin depths irradiated with 300 and 360 mJ (Figs. 11, 12, 13, and 14, respectively) showed flatter surfaces with opened tubules and the absence of smear layer.

Figure 5. SEM micrograph of superficial dentin subsurface irradiated with 160 mJ

Figure 6. SEM micrograph of deep dentin subsurface irradiated with 160 mJ

Figure 7. SEM micrograph of superficial dentin subsurface irradiated with 200 mJ

Figure 8. SEM micrograph of deep dentin subsurface irradiated with 200 mJ

Figure 9. SEM micrograph of superficial dentin subsurface irradiated with 260 mJ

Figure 10. SEM micrograph of deep dentin subsurface irradiated with 260 mJ

Figure 11. SEM micrograph of superficial dentin subsurface irradiated with 300 mJ

Figure 12. SEM micrograph of deep dentin subsurface irradiated with 300 mJ

Figure 13. SEM micrograph of superficial dentin subsurface irradiated with 360 mJ

Figure 14. SEM micrograph of deep dentin subsurface irradiated with 360 mJ

DISCUSSION

The results obtained in this study indicated a decrease in the microhardness values of both superficial and deep dentin, in the tissues underneath the floor of the cavities prepared by Er:YAG laser using higher energy levels (mainly 260 mJ, 300 mJ and 360 mJ). In the face of such situation, it is quite possible to consider that the three highest energies were the most influent in the response of the microhardness. This finding reinforces previous statements [2, 9] that, although the use of high energy levels in dentin accelerates the ablation process, it reduces the mechanical properties of the irradiated substrates.

It is already known that the interaction of lasers with tissue components determines their main effect in biologic tissues. In human dentin, basically composed of water, hydroxyapatite and organic matrix [21], the Er:YAG laser provides efficient ablation rates since the incident energy is highly absorbed by both water and hydroxyapatite [18, 37]. Thus, the absorbed energy is transformed into mounting pressure inside the tissue, occurring successive microexplosions, which causes the removal of tissue components [38]. However, the elimination of the mineral phase from dentin surfaces modifies their morphology and mechanical properties [28, 32, 36], having a positive correlation between hardness and

mineral content [39]. Moreover, changes in hardness and tissue composition produced by high Er:YAG laser energy levels may be related to the denaturation of the dentin organic matrix, with a strong modification of the collagen chain [40].

Additionally, it has been reported [41] that Er:YAG laser radiation modifies the calcium-to-phosphorus ratio. Besides, increased energies produce surface irregularities with greater ablation of intertubular dentin, which resulted in a protruded appearance of peritubular dentin and the opening of dentinal tubules [37]. Since peritubular dentin is highly mineralized [26], the thermal effects, the changes in size and the ultrastructure of apatite crystals probably corroborate the microhardness changes [42]. This way, the intense removal and/or modification of both inorganic and organic structures would become the substrate less resistant to local deformations under load conditions, which may explain the reduction in the dentin microhardness values after being irradiated with the high energy levels used in this study.

A significant increase in microhardness values was found only in the closest point (until 20 μm) under the floor of cavities prepared in superficial dentin using the lowest energy level (160 mJ). As already described above, the higher the energy, the higher the ablation rate, but causing evident alterations in the organic structures. Then, it may be considered that 160 mJ promoted lower tissue removal with unremarkable damages in the organic matrix, which could have increased the proportion of the mineral content. Additionally, this most superficial layer has a natural increased stiffness because its abundant intertubular dentin presents a more homogeneous distribution of the mineral phase within the collagen matrix [43].

In this study, the subsurface microhardness obtained at each point under the cavity floor was increasing throughout the full extent. This shows that during Er:YAG laser irradiation, almost all incident energy is consumed in the ablation process, which limits the

deleterious thermal side effects in the tissues under the irradiated surface, especially under water [10, 11, 13, 14].

Taking into account the dentin depths, the superficial dentin microhardness was higher than deep dentin, thus accepting the hypothesis that, as in sound dentin [43], the decreased hardness near the pulp could be explained by a decrease in the hardness of the intertubular dentin matrix. Thus, it is likely that the intertubular dentin near the pulp is less mineralized [26] and influence the resistance to deformation of these substrates after being submitted to the ablation process by Er:YAG laser.

The clinical application of the knowledge on the mechanical properties of dentin under normal and altered conditions would help the adhesive restorative treatment [37, 44], since there is a strong relationship between dentin microhardness and bond strength [39]. Adhesive restorations are more retained by hard dentin due to their better mechanical stability, which indicates that microhardness may provide a first step towards predicting the behavior of dentin/restorations interfaces [24, 36], besides being a quantitative method to predict variations in the mineral content of dentin irradiated by Er:YAG laser [45].

CONCLUSIONS

Based on the results obtained, it may be concluded that the lowest energy level increased superficial dentin microhardness until the closest point under cavity preparation; deep dentin subsurface microhardness was not altered by 160 and 200 mJ, while higher energy levels reduced subsurface microhardness of both superficial and deep dentin.

REFERENCES

1. Dostálová T, Jelinková H, Krejsa O, Hamal K, Kubelka J, Kugerova H, Procházka S (1998) Noncontact Er:YAG laser ablation: clinical evaluation. *J Clin Laser Med Surg* 16:273-282
2. Hibst R (2002) Lasers for caries removal and cavity preparation: state of the art and future directions. *J Oral Laser Appl* 2:203-211
3. Takamori K, Furukawa H, Morikawa Y, Katayama T, Watanabe S (2003) Basic study on vibrations during tooth preparations caused by high-speed drilling and Er:YAG laser irradiation. *Lasers Surg Med* 32:25-31
4. Attrill DC, Davies RM, King TA, Dickinson MR, Blinkhorn AS (2004) Thermal effects of the Er:YAG laser on a simulated dental pulp: a quantitative evaluation of the effects of a water spray. *J Dent* 32:35-40
5. Chinelatti MA, Ramos RP, Chimello DT, Borsatto MC, Pécora JD, Palma-Dibb RG (2004) Influence of the use of Er:YAG laser for cavity preparation and surface treatment in microleakage of resin-modified glass ionomer restorations. *Oper Dent* 29:430-436
6. Chinelatti MA, Ramos RP, Chimello DT, Corona SA, Pécora JD, Palma-Dibb RG (2006) Influence of Er:YAG laser on cavity preparation and surface treatment in microleakage of composite resin restorations. *Photomed Laser Surg* 24:214-218
7. Wigdor HA, Walsh JT, Featherstone JD, Visuri SR, Fried D, Waldvogel JL (1995) Lasers in dentistry. *Lasers Surg Med* 16:103-133
8. Cozean C, Arcoria CJ, Pelagalli J, Powell L (1997) Dentistry for the 21st century? Erbium:YAG laser for teeth. *J Am Dent Assoc* 128:1080-1087
9. Bader C, Krejci I (2006) Marginal quality in enamel and dentin after preparation and finishing with an Er:YAG laser. *J Dent* 19:337-342

10. Hibst R, Keller U (1989) Experimental studies of the application of the Er:YAG laser on dental hard substances: I. Measurement of the ablation rate. *Lasers Surg Med* 9:338-344
11. Matsumoto K, Nakamura Y, Mazeki K, Kimura Y (1996) Clinical dental application of Er:YAG laser for class V cavity preparation. *J Clin Laser Med Surg* 14:123
12. Matsumoto K, Wang X, Zhang C, Kinoshita JI (2007) Effect of a novel Er:YAG laser in caries removal and cavity preparation: A clinical observation. *Photomed Laser Surg* 25:8-13
13. Hossain M, Nakamura Y, Kimura Y, Nakamura G, Matsumoto K (1999) Ablation depths and morphological changes in human enamel and dentin after Er:YAG laser irradiation with or without water mist. *J Clin Laser Med Surg* 17:105-109
14. Gimbel CB (2000) Hard tissue laser procedures. *Dent Clin North Am* 44:931-953
15. Kim JM, Kim ME, Kim KS (2005) Ablation rate and intrapulpal temperature by irradiation with Er:YAG laser. *Korean J Oral Med* 9:375-381
16. Jelinková H, Dostalová T, Krejsa O, Hamal K, Kubelka J, Procházka S (1997) The influence of Er:YAG laser ablation on cavity surface and cavity shape. *SPIE Proc* 2672:193-196
17. Armengol V, Jean A, Marion D (2000) Temperature rise during Er:YAG and Nd:YAG laser ablation of dentin. *J Endodont* 26:138-141
18. Mercer CE, Anderson P, Davis GR (2003) Sequential 3D X-ray microphotographic measurement of enamel and dentine ablation by an Er:YAG laser. *Br Dent J* 25:99-104
19. Lizarelli RF, Kurachi C, Misoguti L, Bagnato VS (1999) Characterization of enamel and dentin response to Nd:YAG picosecond laser ablation. *J Clin Laser Med Surg* 17:127-131

20. Raum K, Kempf K, Hein HJ, Schubert J, Maurer P (2007) Preservation of microelastic properties of dentin and tooth enamel in vitro--a scanning acoustic microscopy study. *Dent Mater* 23:1221-1228
21. Marshall GW Jr (1993) Dentin: microstructure and characterization. *Quintessence Int* 24:606-617
22. Balooch G, Marshall GW, Marshall SJ, Warren OL, Asif SA, Balooch M (2004) Evaluation of a new modulus mapping technique to investigate microstructural features of human teeth. *J Biomech* 37:1223-1232
23. Habelitz S, Rodriguez BJ, Marshall SJ, Marshall GW, Kalinin SV, Gruverman A (2007) Peritubular dentin lacks piezoelectricity. *J Dent Res* 86:908-911
24. Marshall GW, Marshall SJ, Kinney JH, Balooch M (1997) The dentin substrate: structure and properties related to bonding. *J Dent Res* 76:441-458
25. Pashley D (1989) Dentin: a dynamic substrate-a review. *Scanning Microsc* 3:161-174
26. Kinney JH, Marshall SJ, Marshall GW (2003) The mechanical properties of human dentin: a critical review and re-evaluation of the dental literature. *Crit Rev Oral Biol Med* 14:13-29
27. Senawongse P, Otsuki M, Tagami J, Mjör I (2006) Age-related changes in hardness and modulus of elasticity of dentine. *Arch Oral Biol* 51:457-463
28. Van Meerbeek B, Willems G, Celis JP, Roos JR, Braem M, Lambrechts P, Vanherle G (1993) Assessment by nanoindentation of the hardness and elasticity of the resin-dentin bonding area. *J Dent Res* 72:1434-1442
29. Kielbassa AM, Wrbas KT, Monting JS, Hellwing E (1999) Correlation of transversal micrography and microhardness on *in situ* induced desmineralization in irradiated and normal human dental enamel. *Arch Oral Biol* 44:243-251

30. Arends J, Schuthof J, Jongebloed W (1980) lesion depth and microhardness indentations on artificial white spot lesions. *Caries Res* 14:190-195
31. Koulourides T, Housch T (1983) Hardness testing and micrography of enamel in relation to intraoral des and remineralization. In Leach SA, Edgar WM *Demineralization and Remineralization of the Teeth*, IRL Press, Oxford, pp 255-72
32. Fuentes V, Toledano M, Osorio R, Carvalho RM (2003) Microhardness of superficial and deep sound human dentin. *J Biomed Mater Res A* 15:850-853
33. Souza AE, Corona SAM, Palma-Dibb RG, Borsatto MC, Pécora JD (2004) Influence of Er:YAG laser on tensile bond strength of a self-etching system and a flowable resin in different dentin depths. *J Dent* 32:269-275
34. Gonçalves M, Corona SA, Palma-Dibb RG, Pécora JD (2007) Influence of pulse repetition rate of Er:YAG laser and dentin depth on tensile bond strength of dentin-resin interface. *J Biomed Mater Res A* 1 “in press”
35. Kim KS, Kim ME, Shin EJ (2005) Irradiation time and ablation rate of enamel in contact and non-contact irradiation with Er:YAG laser. *Photomed Laser Surg* 23:216-218
36. Toledano M, Osorio R, Osorio E, Prati C, Carvalho RM (2005) Microhardness of acid-treated and resin infiltrated human dentine. *J Dent* 33:349-354
37. Corona SAM, Souza AE, Chinelatti MA, Borsatto MC, Pecora JD, Palma-Dibb RG (2007) Effect of energy and pulse repetition rate of Er:YAG laser on dentin ablation ability and morphological analysis of the laser-irradiated substrate. *Photomed Laser Surg* 25:26-33
38. Lee BS, Lin CP, Hung YL, Lan WH (2004) Structural changes of Er:YAG laser-irradiated human dentin. *Photomed Laser Surg* 22:330-334

39. Panighi M, G'Sell C (1992) Influence of calcium concentration on the dentin wettability by an adhesive. *J Biomed Mater Res* 26:1081–1089
40. Ceballos L, Osorio R, Toledano M, Tay FR, Marshall GW (2002) Bonding to Er:YAG laser treated dentin. *J Dent Res* 81:119-122
41. Hossain M. (2000) Caries-preventive effect of Er:YAG laser irradiation with or without water mist. *J Clin Laser Med Surg* 18:61- 65
42. Arimoto N, Suzaki A, Sakuma K, Kashiwara S, Yamada M, Senda A (1999) Micro structural changes in dentin irradiated Er:YAG laser. *J Dent Res* 78:316 (Abstract 1703)
43. Kinney JH, Balooch M, Marshall SJ, Marshall GW Jr, Weihs TP (1996) Hardness and Young's modulus of human peritubular and intertubular dentine. *Arch Oral Biol* 41:9-13
44. Xu HHK, Smith DT, Jahanmir S, Romberg E, Kelly JR, Thompson VP, Rekow DE (1998) Indentation damage and mechanical properties of human enamel and dentin. *J Dent Res* 77:472-480
45. Hossain M, Nakamura Y, Tamaki Y, Yamada Y, Murakami Y, Matsumoto K (2003) Atomic analysis and knoop hardness measurements of the cavity floor prepared by Er,Cr:YSGG laser irradiation in vitro. *J Oral Rehabil* 30:515-521

Conclusões

5. CONCLUSÕES GERAIS

Com base nos resultados obtidos neste estudo, pode-se concluir que:

- a capacidade de ablação da dentina foi diretamente relacionada com o nível de energia do laser Er:YAG utilizado para a realização de preparos cavitários e não dependeu da profundidade do substrato;
- morfológicamente pôde-se observar que na dentina profunda ocorreu uma ablação mais seletiva, com menor remoção da dentina peritubular;
- a microdureza da dentina foi influenciada pela profundidade do substrato e pelo nível de energia de irradiação do laser Er:YAG;
- na dentina superficial, a energia de 160 mJ promoveu um aumento na microdureza da região mais próxima ao preparo;
- a microdureza da dentina profunda não foi alterada quando foram utilizadas as energias de 160 e 200 mJ, enquanto os níveis de energia superiores promoveram uma diminuição na microdureza de ambas as dentinas.

*Referências
Bibliográficas*

REFERÊNCIAS BIBLIOGRÁFICAS

AOKI, A.; ISHIKAWA, T.; YAMADA, M.; OTSUKI, K.; WATANABE, H. TAGAMI, J.; ANDO, Y. YAMAMOTO, H. Comparison between Er:YAG laser and conventional technique for root caries treatment in vitro. **Journal of Dental Research**, v.77, n.6, p.1404-1414, 1998.

APEL, C.; MEISTER, N.; SCHMITT, H.; GRABER, G.; GUTKNECHT, N. Calcium Solubility of Dental Enamel following Sub-ablative Er:YAG and Er:YSGG laser irradiation in vitro. **Lasers in Surgery and Medicine**, v.30, p.337-341, 2002.

ARENDS, J.; SCHUTHOF, J.; JONGEBLOED, W. lesion depth and microhardness indentations on artificial white spot lesions. **Caries Research**, v.14, n.4, p.190-195, 1980.

ARIAMOTO, A.; SUZAKI, A.; SAKUMA, K.; KASHIHARA, S.; YAMADA, M.; SENDA, A. Microestrutural changes in dentin irradiated by Er:YAG laser. **Journal of Dental Research**, v.78, p.316, 1999.

ARMENGOL, V.; JEAN, A.; MARION, D. Temperature rise during Er:YAG and Nd:YAG laser ablation of dentin. **Journal of Endodontics**, v.26, n.3, p.138-141, 2000.

ARMENGOL, V.; JEAN, A.; ROHANIZADEH, R.; HAMEL, H. Scanning electron microscopic analysis of diseased and healthy dental hard tissues after Er:YAG laser irradiation: in vitro study. **Journal of Endodontics**, v.25, n.8, p.543-546, 1999.

ATTRILL, D.C.; DAVIES, R.M.; KING, T.A.; DICKINSON, M.R.; BLINKHORN, A.S. Thermal effects of the Er:YAG laser on a simulated dental pulp: a quantitative evaluation of the effects of a water spray. **Journal of Dentistry**, v.32, p.35-40, 2004.

CEBALLOS, L. OSORIO, R.; TOLEDANO, M.; TAY, F. R.; MARSHALL, G.W. Shear bond strength of composite bonded to different treated dentin surfaces. **Journal of Dental Research**, v.80, p.528., 2001.

CEBALLOS, L.; OSORIO, R.; TOLEDANO, M.; TAY, F. R.; MARSHALL, G.W. Bonding to Er:YAG laser treated dentin. **Journal of Dental Research**, v.81, p.119-122, 2002.

CHIMELLO, D.T.; PALMA DIBB, R.G.; BORSATTO, M.C.; CORONA, S.A.M.; PECORA, J.D. Efeito do laser Er:YAG sobre a resistencia adesiva de um sistema restaurador. **Pesquisa Odontológica Brasileira**, v.15, Supl., p.157, 2001.

CHINELATTI, M.A.; RAMOS, R.P.; CHIMELLO, D.T.; BORSATTO, M.C.; PECORA, J.D.; PALMA-DIBB, R.G. Influence of the use of Er:YAG laser for cavity preparation and surface treatment in microleakage of resin-modified glass ionomer restorations. **Operative Dentistry**, v.29, n.4, p.430-436, 2004.

CHINELATTI, M.A.; RAMOS, R.P.; CHIMELLO, D.T.; BORSATTO, M.C.; PECORA, J.D.; PALMA-DIBB, R.G. Effect of Er:YAG laser on Microleakage of composite resin restorations. **Journal of Dental Research**, v.82, Spec. Iss. C, p.213, 2003.

CHINELATTI, M.A. **Análise quantitativa *in vitro* da microinfiltração marginal em restaurações classe V com materiais restauradores adesivos. Influência do uso do laser de Er:YAG no preparo cavitário.** 2003. 124p. Dissertação Mestrado- Faculdade de Odontologia de Ribeirão Preto da Universidade de São Paulo. Ribeirão Preto.

CORONA, S. A. M.; BORSATTO, M.C.; PALMA DIBB, R.G. RAMOS, R.P.; PECORA, J.D. Microleakage of class V resin composite restorations after bur, air-abrasion or Er:YAG laser preparation. **Operative Dentistry**, v.26, p.491-497, 2001.

CORONA, S.A.M. **Influência da energia e frequência de pulsos do laser Er:YAG na capacidade de ablação do esmalte e da dentina e análise morfológica superficial. Avaliação *in vitro*.** 2003. 99 p. Tese Livre-Docencia - Faculdade de Odontologia de Ribeirao Preto da Universidade de Sao Paulo, Ribeirao Preto.

COZEAN, C.; ARCORIA, C.J.; PELAGALLI, J.; POWELL, L. Dentistry for the 21 st century? Erbium: YAG laser for teeth. **Journal American of Dental Association**, v.128, p.1080-1087, 1997.

DOSTALOVA, T.; JELINKOVA, H.; KREJSA, O.; HAMAL, K.; KUBELKA, J.; KUGEROVA, H.; PROCHAZKA, S. Noncontact Er:YAG laser ablation: clinical evaluation. **Journal of Clinical Laser Medicine and Surgery**, v. 16, n. 5, p. 273-282, 1998.

FUENTES V.; TOLEDANO M.; OSORIO R.; CARVALHO R.M. Microhardness of superficial and deep sound human dentin. **Journal Biomedical Material Research**, v.15, n.4, p.850-853, 2003.

GIMBEL, C.B. Hard tissue laser procedures. **Dental Clinics of North America**, v.44, n.4, p.931-953, 2000.

HIBST, R. J Lasers for caries removal and cavity preparation: state of the art and future directions. **Oral Laser Applications** v.2, n.4, p.203-211, 2002.

HIBST, R.; KELLER, U. Experimental studies application of the Er:YAG laser on dental hard substances. **Proceedings SPIE**, Barcelona, v.2623, p.139-144, 1995.

HIBST, R.; KELLER, U. Experimental studies of the application of the Er:YAG laser on dental hard substances: I. Measurement of the ablation rate. **Lasers in Surgery and Medicine**, v.9, p.334-338, 1989.

HOSSAIN, M.; NAKAMURA, Y.; YAMADA, Y.; KIMURA, Y.; NAKAMURA, G.; MATSUMOTO, K. Ablation depths and morphological changes in human enamel and dentin after Er:YAG laser irradiation with and without water mist. **Journal of Clinical Laser Medicine and Surgery**, v.17, n.3, p.105-109, 1999.

HOSSAIN, M.; NAKAMURA, Y.; KIMURA, Y.; YAMADA, Y.; ITO, M.; MATSUMOTO, K. Caries-preventive effect of Er:YAG laser irradiation with or without water mist. **Journal Clinical of Laser Medicine and Surgery**, v. 18, n. 2, p. 61-65, 2000.

JELINKOVA, H.; DOSTALOVA, T.; KREJSA, O.; HAMAL, K.; KUBELKA, J.; PROCHAZKA, S. The influence of Er:YAG laser ablation on cavity surface and cavity shape. In: International Society for Optical Engineering, **Proceedings SPIE**, v. 2672, p.193-196, 1996.

KAMEYAMA, A ., KOGA, H., TAKIZAWA, M., TAKAESU, Y., HIRAI, Y. Effect of Er:YAG laser on acid resistance to bovine dentin *in vitro*. **Bulletin of Tokyo Dental College**, v.41, n.2, p.43-48, 2000.

KATAUMI, M. NAKAJIMA, M.; YAMADA, T., TAGAMI, J. Tensile bond strength and SEM evaluation of Er:YAG laser irradiated dentin using dentin adhesive. **Dental Materials Journal**, v. 17, n. 2, p. 125-138, 1998.

KELLER, U.; HIBST, R. Experimental studies of the application of the Er:YAG laser on dental hard substances: II. Light microscopic and SEM investigations. **Lasers in Surgery and Medicine**, v. 9, n. 4, p. 345-351, 1989.

KELLER, U.; HIBST, R. Er:YAG laser effects on soft and hard dental tissues. In: MISERANDINO, L.J.; PICK, R.M. **Laser in Dentistry**. Chicago: Quintessence, cap.11, p.161-172, 1995.

KIELBASSA, A.M.; WRBAS, K.T., MONTING, J.S.; HELLWING, E. Correlation of transversal micrography and microhardness on *in situ* induced desmineralization in irradiated and normal human dental enamel. **Archives of Oral Biology**, v. 44, n.3, p.243-251, 1999.

KIM, M.E.; JEOUNG, D.J.; KIM, K.S. Effects of water flow on dental hard tissue ablation using Er:YAG laser. **Journal of Clinical Laser Medicine and Surgery**, v. 21, n. 3, p. 139-144, 2003.

KOULORIDES, T.; HOUSCH, T. Hardness testing and micrography of enamel in relation to intraoral des and remineralization. In: Leach, S.A.; Edgar, W.M. **Demineralization and Remineralization of the teeth**, Oxford, IRL Press, p.255-272, 1983.

KUMAZAKI, M. Removal of hard dental (cavity preparation) with the Er:YAG laser. In: International Congress on Lasers in Dentistry, 6th Congress of the International Society for Lasers in Dentistry, **Proceedings SPIE**, p. 12-16, 1998.

LI, Z.Z.; CODE, J.E.; VAN DE MERWE, W.P. Er:YAG laser ablation of enamel and dentin of human teeth: determination of ablation rates at various fluences and pulses repetition rates. **Laser in Surgery and Medicine**, v. 12, n. 6, p. 625-630, 1992.

MARTINEZ-INSUA, A.; DA SILVA DOMINGUEZ, L; RIVERA, F.G.; SANTANA-PENIN, U.A. Differences in bonding to acid-etched or Er: YAG-laser-treated enamel and dentin surfaces. **Journal of Prosthetic Dentistry**, v. 84, n. 3, p.280-288, 2000.

MATSUMOTO, K.; NAKAMURA, Y.; MAZEKI,K.; KIMURA, Y. Clinical dental application of Er:YAG laser for class V cavity preparation. **Journal of Clinical Laser Medicine and Surgery**, v.14, n.13, p.123-127, 1996.

MEHL, A.; KREMERS, L.; SALZMANN, K.; HICKEL, R. 3D volume-ablation rate and thermal side effects with the Er:YAG and Nd:YAG laser. **Dental Materials**, v.13, n. 4, p. 246-251, 1997.

MERCER, C.E.; ANDERSON, P.; DAVIS, G.R. Sequential 3D X-ray microtomographic measurement of enamel and dentine ablation by an Er:YAG laser. **British Dental Journal**, v. 25, n. 2, p. 99-104, 2003.

MONGHINI, E. M., WANDERLEY, R. L., PECORA, J. D., PALMA-DIBB, R. G., CORONA, S. A. M., BORSATTO, M. C. Bond strength to dentin of primary teeth irradiated with varying Er:YAG laser energies and SEM examination of the surface morphology. **Lasers in Surgery and Medicine**, v.34, n.3, p.254-259, 2004.

PALMA-DIBB, R.G.; CORONA, S.A.M., BORSATTO, M.C.; RAMOS, R.P.; FERREIRA, K.C., PECORA, J.D. Assessing microleakage on class V composite resin restorations after Er:YAG laser preparation varying the adhesive systems. **Journal of Clinical Laser Medicine and Surgery**, v.20, n.3, p.129-133, 2002.

RAMOS, R.P.; PALMA-DIBB, R.G.; CHIMELLO, D.T.; CHINELATTI, M.A.; PECORA, J.D. Effect of Er:YAG laser on bond strength to dentin of a self-etching primer and two single-bottle adhesive systems. **Lasers in Surgery and Medicine**, v.31, n.3, p.164-170, 2002.

SAKAKIBARA, Y.; ISHIMARU, K.; ASANO, S.; TAKAMIZU, M.; KOHNO, A. Morphological changes of tooth surface irradiated by Er:YAG laser. In: The International Congress on Lasers in Dentistry, 4., Cingapura. **Proceedings...** p.163-166, 1994.

SHIGETANI, Y.; TATE, Y.; OKAMOTO, A.; IWAKU, M.; ABU-BAKR, N. A study of cavity preparation by Er:YAG laser. Effects on the marginal leakage of composite resin restoration. **Dental Materials Journal**, v. 21, n. 3, p. 238-249, 2002

SOUZA, A. E., CORONA, S. A. M., PALMA-DIBB, R. G., BORSATTO, M. C., PECORA, J. D. Influence of Er:YAG laser on tensile bond strength of a self-etching system and a flowable resin in different dentin depths. **Journal of Dentistry**, v.32, p. 269-275, 2004.

SULEWSKI, J.G. Histological survey of laser dentistry. **Dental Clinics of North America**, v.44, n.4, p.717-752, 2000.

TAKAMORI, K. A. A histopatological and himmunohistochemical study of dental pulp nerve fibers in rats after cavity preparation using Er:YAG laser. **Journal of Endodontics**, v.26, p.95-99, 2000.

TANJI, E.Y. **Alterações morfológicas do esmalte e dentina de cavidades classe I preparadas com laser Érbio:YAG – Estudo *in vitro***. 1998. 60p. Dissertação Mestrado - Faculdade de Odontologia da Universidade de Sao Paulo, Sao Paulo.

VISURI, S.R; GILBERT, J.L.; WRIGHT, D.D; WIGDOR, H.A.; WALSH, J.T. Shear strength of composite bonded to Er:YAG laser-prepared dentin. **Journal of Dental Research**., v.75, n.1, p.599-605, 1996.

Anexos

ANEXO 1

UNIVERSIDADE DE SÃO PAULO
FACULDADE DE ODONTOLOGIA DE RIBEIRÃO PRETO
COMITÊ DE ÉTICA EM PESQUISA
Avenida do Café, s/nº - Telefone: (016) 3602-3970
14040-904 - Ribeirão Preto - SP - Brasil
Fax: (016) 3633-0999

Of.CEP/19305/FORP/240805
MLCK/mlck

Prezado (a) Professor (a),

Ref. Processo n. 2005.1.656.58.1

De ordem da Senhora Coordenadora do Comitê de Ética em Pesquisa desta Faculdade, informamos que o referido Comitê, em sua 60ª Sessão realizada no dia 24 de agosto de 2005, deliberou **aprovar** o Projeto de Pesquisa envolvendo seres humanos intitulado: **"Influência da energia do laser Er:YAG na capacidade de ablação, microdureza e morfologia da dentina superficial e profunda"**, a ser desenvolvido por Vossa Senhoria, na Faculdade de Odontologia de Ribeirão Preto, devendo o atestado para publicação final, ser expedido pelo Comitê de Ética em Pesquisa, após a entrega e aprovação do Relatório Final pelo referido Comitê.

Na oportunidade, lembramos da necessidade de entregar na Seção de Expediente e Protocolo, com o formulário preenchido pelo pesquisador responsável, o **Relatório Parcial no dia 30 de agosto de 2006** e o **Relatório Final no dia 30 de agosto de 2007**.

Atenciosamente,

Maria Lúcia Câmara Kühl
Secretária do Comitê de Ética em Pesquisa

Il.^{ma}. Sr.^a.

Prof.^a. Dr.^a. REGINA GUENKA PALMA DIBB

Professor Associado do Departamento de Odontologia Restauradora -
FORP/USP

ANEXO 2

Mensagem de Impressão do Windows Live Hotmail

Página 1 de 3

Fwd: [Fwd: Photomedicine and Laser Surgery - Decision on Manuscript ID PHO-2007-2201]

De: **Michelle Chinelatti** (michinelatti@gmail.com)
Enviada: quinta-feira, 3 de janeiro de 2008 17:38:54
Para: Michelle Chinelatti (michinelatti@hotmail.com)

----- Forwarded message -----

From: **Regina Guenka Palma Dibb** <rgpalma@forp.usp.br>
Date: 20/12/2007 14:09
Subject: [Fwd: Photomedicine and Laser Surgery - Decision on Manuscript ID PHO-2007-2201]
To: michinelatti@gmail.com

19-Dec-2007

Dear Dr. Palma-Dibb:

Manuscript ID PHO-2007-2201 entitled "Ablation rate and morphology of superficial and deep dentin irradiated with different energies of Er:YAG laser" which you submitted to Photomedicine and Laser Surgery, has been reviewed. The comments of the reviewer(s) are included at the bottom of this letter.

The reviewer(s) have recommended revisions to your manuscript. Therefore, I invite you to respond to the reviewer(s)' comments and revise your manuscript.

To revise your manuscript, log into <http://mc.manuscriptcentral.com/photomedicine> and enter your Author Center, where you will find your manuscript title listed under "Manuscripts with Decisions." Under "Actions," click on "Create a Revision." Your manuscript number has been appended to denote a revision.

You will be unable to make your revisions on the originally submitted version of the manuscript. Instead, revise your manuscript using a word processing program and save it on your computer. Please also highlight the changes to your manuscript within the document by using the track changes mode in MS Word or by using bold or colored text. Once the revised manuscript is prepared, you can upload it and submit it through your Author Center.

When submitting your revised manuscript, you will be able to respond to the comments made by the reviewer(s) in the space provided. You can use this space to document any changes you make to the original manuscript. In order to expedite the processing of the revised manuscript, please be as specific as possible in your response to the reviewer(s).

As our readership is largely English-speaking we ask that all manuscripts be reviewed carefully for English grammar and syntax.

IMPORTANT: Your original files are available to you when you upload your revised manuscript. Please delete any redundant files before completing the submission.

Because we are trying to facilitate timely publication of manuscripts submitted to Photomedicine and Laser Surgery, your revised manuscript should be uploaded as soon as possible. If it is not possible for you to submit your revision in a reasonable amount of time, we may have to consider your paper as a new submission.

Once again, thank you for submitting your manuscript to Photomedicine and Laser Surgery and I look forward to receiving your revision.

<http://by139w.bay139.mail.live.com/mail/PrintShell.aspx?type=message&cpids=bd2b3...> 29/1/2008

Submissions Being Processed for Author Michelle Chinelatti

Page: 1 of 1 (1 total submissions)

Display 10 results per page.

Action	Manuscript Number	Title	Initial Date Submitted	Status Date	Current Status
Action Links		Effect of Er:YAG laser energies on superficial and deep dentin microhardness	Jan 29, 2008	Jan 29, 2008	Submitted

Page: 1 of 1 (1 total submissions)

Display 10 results per page.

<< Author Main Menu

ANEXO 3